



MOTIVE DEEP CYCLE AGM

BATTERIES


SDC6-265-GC2 (6volts)



SDC SERIES - SUPERIOR CYCLYING NON SPILLABLE

6V 265Ah





General Features



- PAM/NAM amount optimization
- 4BS crystal paste mixing & curing technology
- Double layer separator technology
- Improved design electrolyte S.G.

Excellent deep cycle performance

- Plate assembly pressure re-engineering
- New PAM/NAM recipe introduced
- Gel electrolyte technology
- Rare earth alloy
- Double layer separator technology
- Lower acid filling temperature

Solve NAM sulphation

- Carbon boost technology
- Pre-sulfate technology

•

Improved PSoC cycling

- Carbon boost technology
- Mix carbon boost technology
- Targeting for higher level through carbon technology



Less water loss

- PAM/NAM amount optimization
- New PAM/NAM recipe introduced
- Rare earth alloy



Delay PAM softening and shedding

- Plate assembly pressure re-engineering
- 4BS crystal paste mixing & curing technology
- Higher paste density



Optimize electrolyte stratification

• Introduce AGM-GEL technology



SPECIFICATIONS


Voltage	6V			
	Length	260mm((10.2 inches)	
Dimension	Width	180mm(ʻ	7.09 inches)	
	Container hei	ght 263mm(10.4 inches)	
	Total Height	268mm	(10.6 inches)	
Approx Weight		32.9	kg (72.5) lbs	
Terminal			T11(M8)	
Container Material			ABS	
Reserve Capacity		25A	620min	
		75A	165 min	
Capacity		20HR	268Ah	
		10HR	240Ah	
		5HR	220Ah	
Operating Temp. Range	Discharge	-20~55	-20~55°C (-4~131°F)	
	Charge	0~40°C (32~104°F)		
	Storage	-15~40	°C (5~104°F)	

Applications


- Arial Work Platforms
- Transportation
- Floor Cleaning Machines
- Solar & Renewable Energy













Relationship of OCV and State of Charge











Starmax Corporation

1585 Cliveden Avenue, Delta, British Columbia V3M 6M1, Canada

Phone: +1 888 669 1310

Email: info@starmaxbatteries.com Website: www.starmaxbatteries.com









